

Data Sheet FLEXABILITY TPA

rev. 2.0 14/01/2019

SUGGESTED PRINT SETS (1)			
Suggested print sets	unit	value	test method
extruder temp	C°	230-250	internal
plate temp	C°	85-100	internal
min. nozzle diameter	mm.	0.4	internal
fan	%	0-30	internal
print speed	mm/I°	30-40	internal
PROPERTY			
Physical			
Specific gravity	g/cm3	I	ISO 1183
Water absorption	%	0.4	ISO 62
Mechanical at 23°C / 50% rh			
Tensile strain at break	MPa	32	ISO 527
Charpy impact (23°C)	kJ/m²	no break	ISO 179
Charpy impact (-30°C)	kJ/m²	no break	ISO 179
Hardness	sh/A - sh/D	74 - 22	ISO 62
Thermal			
Melting point	°C	134	ISO 11357
Vicat softening temp.	°C	58	ISO 306

Disclaimer

The above information is provide in good fact .Treedfilaments is not responsable for any processing which may occur to product finished articles , packaging materials and other .

Further Treedfilaments makes no warranty or representation of any kind regarding the information given or the product described and expressly disclaims all implied warranties , representations and conditions , including without limitation all warranties and conditions of quality , merchantability and suitability or fitness for particular purpose .



Data Sheet FLEXABILITY TPA

rev. 2.0 14/01/2019

ADDITIONAL INFORMATIONS

In general filaments made with Flexability (TPA) can be processed on conventional 3D printer using FDM / FFF technology.

Flexability (TPA) is a special elastomer polyamide based developed for 3D printing and to obtain best results we recommend pre drying the filaments at 65° for 2 h. Increase drying time for spools up 1 kg.

Don't leave the filament stopped inside the nozzle more than 20 min. If that down the temperature under 210°, better stop the thermal control.

(1) Suggested print set merely represent a recommendation for general use . Every printer necessity a specific set , nozzle temp, bed temp, etc .

Disclaimer

The above information is provide in good fact .Treedfilaments is not responsable for any processing which may occur to product finished articles , packaging materials and other .

Further Treedfilaments makes no warranty or representation of any kind regarding the information given or the product described and expressly disclaims all implied warranties, representations and conditions, including without limitation all warranties and conditions of quality, merchantability and suitability or fitness for particular purpose.